

(11)Publication number:

10-244166

(43) Date of publication of application: 14.09.1998

(51)Int.CI.

B01J 35/02 A61L 9/01 B01J 21/06 B01J 37/02 C₀₂F

(21)Application number: 09-063867

(71)Applicant: AGENCY OF IND SCIENCE &

TECHNOL J M II KK

TOUGEDA HIROSHI NONAMI TOORU

(22)Date of filing:

03.03.1997

(72)Inventor: TOUGEDA HIROSHI

NONAMI TOORU ARAMAKI FUJIO ARAMAKI SHOSHICHI

(54) ENVIRONMENT CLEANING MATERIAL AND ITS PRODUCTION

(57) Abstract:

PROBLEM TO BE SOLVED: To effectively and safely carry out the cleaning of environment such as the removal of a malodor, the decomposition and removal of a harmful material or contaminant in air or the treatment of waste water by coating the surface of a substrate whose surface is made of titanium dioxide with a porous calcium phosphate film.

SOLUTION: Water and nitric acid are added to titanium tetraisopropoxide to prepare a transparent titanium dioxide sol and granular alumina as a carrier is dip-coated with the sol and fired at 550° C. These processes are repeated three times to form a substrate surface-coated with a titanium dioxide film. The surface of the substrate is then coated with a porous calcium phosphate film. The resultant environment cleaning material enables the cleaning of environment such as the removal of a malodor, the decomposition and removal of a harmful material or contaminant in air, the treatment of waste water, the purification of water or antibacterial and antimold treatment in an effective, profitable and safe manner.

LEGAL STATUS

[Date of request for examination]

03.03.1997

[Date of sending the examiner's decision of

rejection]

[Kind of final disposal of application other than

the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] [Date of registration] 3275032

08.02.2002

[Number of appeal against examiner's decision

of rejection]

[Date of requesting appeal against examiner's decision of rejection] [Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office